arXiv:cond-mat/9912212v1 [cond-mat.str-el] 13 Dec 1999

Competing Ground States of the New Class of Halogen-Bridged Metal Complexes

Shoji Yamamoto
Department of Physics, Okayama University, Tsushima, Okayama 700-8530, Japan

(Received 7 October 1999)

Based on a symmetry argument, we study the ground-state properties of halogen-bridged binuclear metal chain complexes. We systematically derive commensurate density-wave solutions from a relevant two-band Peierls-Hubbard model and numerically draw the the ground-state phase diagram as a function of electron-electron correlations, electron-phonon interactions, and doping concentration within the Hartree-Fock approximation. The competition between two types of charge-density-wave states, which has recently been reported experimentally, is indeed demonstrated.

PACS numbers: 71.10.Hf, 71.45Lr, 75.30.Fv, 03.65.Fd

Halogen-bridged transition-metal linear-chain complexes (MX chains; M = metal, X = halogen) have been a central subject in material science due to their low dimensionality and competing electron-electron (el-el) and electron-phonon (el-ph) interactions, which lead to the variety of electronic states. PtX compounds [1] provided various topics of both chemical and physical interest, such as intense dichroism and unusual Raman spectra which originate in their mixed-valence ground states. NiX compounds [2–4] with mono-valence magnetic ground states visualized the competition between the Peierls and Mott insulators. Nasu [5] gave a theoretical description of the ground-state competition. The Los Alamos group [6] extensively investigated potential ground states, including incommensurate density waves [7] and spin-frustrated novel antiferromagnetism [8].

In recent years, the new class of these family compounds (MMX chains), which consists of binuclear metal units bridged by halogen ions, has been stimulating further interest in this system. The presence of the metal-metal bonds allows us to expect a wider variety of electronic structures [9–11]. $\mathrm{K_4[Pt_2(pop)_4X]}\cdot n\mathrm{H_2O}$ ($\mathrm{X}=\mathrm{Cl,Br,I}$; $\mathrm{pop}=\mathrm{P_2O_5H_2}$) [12,13] and $\mathrm{M_2(dta)_4I}$ ($\mathrm{M}=\mathrm{Pt,Ni}$; $\mathrm{dta}=\mathrm{CH_3CS_2}$) [14] are both typical of the MMX compounds but their electronic properties look rather different. $\mathrm{Pt_2(dta)_4I}$ shows metallic conduction above room temperature [11], whereas no metallic behavior has ever been found in the pop series. Their ground states are both charge density waves [9–11] but show different valence structures. The variety of ground states must be one of the most interesting consequences of intrinsic multi-band effects and competing el-el and el-ph interactions. Here, based on a symmetry argument [15–17], we reveal rich phase diagrams of the one-dimensional (1D) two-band three-orbital Peierls-Hubbard model. *The competition between the two distinct charge-density-wave states is indeed demonstrated. Antiferromagnetic ground states for the Ni complexes and the onset of further novel phases under hole doping are also predicted.*

We introduce the 1D model Hamiltonian as

$$\begin{aligned}
\mathcal{H} =& \sum_{n,s}\left[(\varepsilon_{\mathrm{M}}-\beta\delta_{1:n})n_{1:n,s}+(\varepsilon_{\mathrm{M}}+\beta\delta_{2:n})n_{2:n,s}+\varepsilon_{\mathrm{X}}n_{3:n,s}\right]+\frac{K}{2}\sum_{n}\left(\delta_{1:n}^2+\delta_{2:n}^2\right)\\
&-\sum_{n,s}\left[(t_{\mathrm{MX}}-\alpha\delta_{1:n})a_{1:n,s}^{\dagger}a_{3:n,s}+(t_{\mathrm{MX}}+\alpha\delta_{2:n})a_{2:n,s}^{\dagger}a_{3:n,s}+t_{\mathrm{MM}}\,a_{1:n,s}^{\dagger}a_{2:n-1,s}+\mathrm{H.c.}\right]\\
&+\sum_{n}\left(U_{\mathrm{M}}\,n_{1:n,+}n_{1:n,-}+U_{\mathrm{M}}\,n_{2:n,+}n_{2:n,-}+U_{\mathrm{X}}\,n_{3:n,+}n_{3:n,-}\right)\\
&+\sum_{n,s,s'}\left(V_{\mathrm{MX}}\,n_{1:n,s}n_{3:n,s'}+V_{\mathrm{MX}}\,n_{2:n,s}n_{3:n,s'}+V_{\mathrm{MM}}\,n_{1:n,s}n_{2:n-1,s'}\right), \qquad (1)
\end{aligned}$$

where $n_{i:n,s}=a_{i:n,s}^{\dagger}a_{i:n,s}$ with $a_{i:n,s}^{\dagger}$ being the creation operator of an electron with spin $s=\pm$ (up and down) for the $\mathrm{M}d_{z^2}$ ($i=1,2$) or $\mathrm{X}p_z$ ($i=3$) orbital in the nth MXM unit, respectively, and $\delta_{i:n}=u_{3:n}-u_{i:n}$ with $u_{i:n}$ being the chain-direction displacement of the metal ($i=1,2$) or halogen ($i=3$) ion in the nth MXM unit. α and β are, respectively, the intersite and intrasite el-ph coupling constants, while K is the metal-halogen spring constant. We assume, based on experimental observations, that the MM units are not deformed ($u_{1:n}=u_{3:n-1}$). ε_{M} and ε_{X} are the on-site energies (electron affinities) of isolated metal and halogen atoms, respectively. The electron hoppings between these levels are modeled by t_{MM} and t_{MX}, whereas the el-el Coulomb interactions by U_{M}, U_{X}, V_{MM}, and V_{MX}. The symmetry group of the system is given by $\mathbf{G}=\mathbf{P}\times\mathbf{S}\times\mathbf{T}$, where $\mathbf{P}=\mathbf{L}\wedge\mathbf{C}_2$ is the space group of a linear chain with $\mathbf{L}$ being the 1D translation group whose basis vector is the unit-cell translation, $\mathbf{S}$ the group of spin-rotation, and $\mathbf{T}$ the group of time reversal. Let $\check{G}$ denote the irreducible real representations of $\mathbf{G}$, where their representation space is spanned by the Hermitian operators